

VAE1480

Face Material

weight	thickness	material
130g ± 5g ISO536	0.07mm ± 0.005mm ISO534	Scratch Film

Liner

80g / m ² ± 5g ISO536	0.067mm ± 0.005mm ISO534	Super calendered semi-gloss white glassine liner
----------------------------------	--------------------------	--

Adhesive

This is a permanent, acrylic based adhesive. This is an adhesive with high initial viscosity and high end viscosity. It has excellent performance on many packaging materials. It can be used for information labels of food, books and periodicals, wine, beverages, electrical appliances and cultural goods.

Peel adhesion

initial adhesion 8 N/25mm or tear off FTM 9 st.st	20 minutes Peel adhesion value on steel at 90 angle 8 N/25mm or tear off FTM 1 st.st	24 hours Released forced value on steel at 90 angle 5 N/25mm or tear off FTM 3 st.st
--	--	--

Temperature

Min. Appl. Temp. 10°C	Service Temp. -35°C ± 90°C (24H after labeling)
-----------------------	---

Applications

It's suitable for scratched labelling.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

Avoid material deformation caused by overheating. It can be applied to various printing methods such as flexographic printing, letterpress printing and screen printing, and has good expressiveness to ink. Excellent die-cutting characteristics on all customary machines.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.