

**BJB5457****Face Material**

| <b>weight</b>                  | <b>thickness</b>    | <b>material</b>  |
|--------------------------------|---------------------|--|
| 40±10%g/m <sup>2</sup> ISO 536 | 0.054±10%mm ISO 534 | Matte opalescent polypropylene film with special coating |

**Liner**

|                                |                     |  |
|--------------------------------|---------------------|--|
| 58±10%g/m <sup>2</sup> ISO 536 | 0.055±10%mm ISO 534 | White glassine treated with super calender |
|--------------------------------|---------------------|--|

**Adhesive**

A general permanent rubber adhesive. It is an adhesive with a relatively high initial tack. Excellent performance on many packaging materials. Can be used for indirect sales of products such as food, electronics and cosmetics.

**Peel adhesion**

|  |  |  |
|--|--|--|
| Initial adhesion<br>18N/25mm FTM 9 st.st | 20 minutes Peel adhesion value on steel at 180° 18N/25mm FTM 1 st.st | 20 minutes Peel adhesion value on steel at 90° 9N/25mm FTM 2 st.st |
|--|--|--|

**Temperature**

|                      |  |
|----------------------|--|
| Min. Appl. Temp. 5°C | Service Temp. -35°C+65°C (after 24hrs) |
|----------------------|--|

**Applications**

The material has a certain degree of tear resistance and chemical corrosion resistance, and is widely used in labels in industries such as washing, cosmetics, daily chemicals, food and electronic labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

**Printing Methods**

Off-white polypropylene film with a paper-like visual effect, with a layer of coating on the surface, suitable for various printing methods such as flexographic printing, letterpress printing, screen printing and thermal transfer printing, and has good expressive power for inks. For product labels with important properties such as water resistance, oil resistance and chemical substances, it has excellent covering performance on dark bottles. Sharp knives should be used in die-cutting, and at the same time, avoid label overflow due to excessive winding tension

**Shelf life**

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23±2°C and 50±5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.