

# BKF6030

## Face Material

weight	thickness	material
45 ± 10%g/m <sup>2</sup> ISO 536	0.06 ± 10%mm ISO 534	Glossy opalescent polypropylene film with special coating

## Liner

weight	thickness	material
42 ± 10%g/m <sup>2</sup> ISO 536	0.03 ± 10%mm ISO 534	Transparent polyester release film

## Adhesive

A general permanent water-based acrylic adhesive. It is an adhesive with a relatively high initial tack. Excellent performance on many packaging materials. Can be used for indirect sales of products such as food, electronics and cosmetics.

## Peel adhesion

Initial adhesion	20 minutes Peel adhesion value on steel at 180°	20 minutes Peel adhesion value on steel at 90°
15N/25mm FTM 9 st.st	15N/25mm FTM 1 st.st	7N/25mm FTM 2 st.st

## Temperature

Min. Appl. Temp.	Service Temp.
10°C	-35°C+90°C (after 24hrs)

## Applications

This label has good transparency and a certain degree of softness, and is often used as drink permanent acrylic pressure-sensitive adhesive, mineral water daily chemical and cosmetic labels. Suitable for high speed labeling

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

## Printing Methods

Its surface has a special coating, which is suitable for a variety of printing methods. Care should be taken during processing to avoid material deformation caused by overheating. During die-cutting, it should be avoided that the label overflows due to excessive winding tension.

### Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.