

WBA7059

Face Material

weight	thickness	material
70 ± 10%g/m ² ISO 536	0.07 ± 10%mm ISO 534	Uncoated white matte paper

Liner

58 ± 10%g/m ² ISO 536	0.053 ± 10%mm ISO 534	Super calendered yellow glassine backing
----------------------------------	-----------------------	--

Adhesive

A general permanent rubber adhesive. It is an adhesive with a high initial viscosity. High-viscosity, permanent rubber-based adhesive, a high-quality hot-melt adhesive suitable for a variety of substrates, with extremely high initial tack and final tack, meeting the needs of applications that require high tack.

Peel adhesion

initial adhesion 14 N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180 angle 16 N/25mm or tear off FTM 1 st.st	20 minutes Peel adhesion value on steel at 90 angle 8 N/ 25mm or tear off FTM 2 st.st
---	--	---

Temperature

Min. Appl. Temp. 10 °C	Service Temp. -15°C ± 65°C (24H after labeling)
------------------------	---

Applications

This product has good adhesion properties and is widely used in price tags, computer printed labels and matte labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

The surface material has excellent ink absorption and is suitable for a variety of printing methods, including laser and inkjet printing. Matte paper with a rough surface, suitable for printing and printing of simple graphics. Used in office, logistics and other industries.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.